




NATURAL ROMAN CEMENT (NRC)

MAKE YOUR OWN HYDRAULIC LIME USING LIME PUTTY OR HYDRATED LIME

Hydraulic Lime blends

 NRC	 Lime	 Sand	28 day strength
1	0	3	3.5 Newtons
2	1	9	3 Newtons
1	1	6	2.5 Newtons
1	2	9	2 Newtons

Approximate values. Adjust NRC and Hydrated Lime according to sand being used and project requirements.

For greater strengths add GGBS (no more than 20%), for lower strengths add more lime.



VAPOUR OPEN

Will not trap moisture in your building

HELPS WINTER LIME PROJECTS